

**Viatec UK Ltd**

# VIAFIX 0/6



**Ideal for instant, permanent repairs to potholes and other defects in asphalt, macadam and concrete even in freezing wet weather and on high speeds roads.**



## DIRECTIONS FOR USE

- Remove mud and loose material or ice.
- After opening the laminate foil bag, **VIAFIX** should be free flowing, if not, return to the supplied together with the purchase receipt.
- Place **VIAFIX** in the area with a shovel or trowel.
- If the repair is in concrete, shallow or tapering to 0, it is advisable to prime the area to be repaired with the **VIAFIX** Primer.
- Level with a rake or trowel allowing the finished level of **VIAFIX** to be about 25% above the surrounding area, allowing for possible different depths in the same defect.
- If conditions are dry or even damp sprinkle with water at approx 0,5 litre per 14 kg of **VIAFIX**.
- Compact to a level, slightly proud, finish with a hand-tamper, vibrating plate, or roller. If the compacted material is below the level of the surrounding area, add more **VIAFIX**, sprinkle with water and compact into existing material. If traffic management is not practicable, simply allow traffic to compact the area.
- If the depth of the pothole is greater than 100mm, it is advisable to carry out the repair in 50-75mm stages.

## STORAGE AND HANDLING

- Each bag contains 14 kg of **VIAFIX**.
- Store indoors in cool, dry conditions. Avoid direct sunlight or exposure to frost.
- Avoid damage to foil bags.
- All material should be used within 24 hours after opening of foil bags.
- Gloves should be worn and direct contact with skin avoided. In the event of contact, use vegetable oil or proprietary hand cleaners.
- Tools may be cleaned with vegetable oil or any other environmental friendly cleaning agent.
- **VIAFIX** must be used within 12 months of purchase as the workability can be reduced on prolonged storage.
- Coverage rate is approximately 0,6 m<sup>2</sup> per 14 kg at 1cm depth.

## GENERAL ADVICE

- **VIAFIX** is suitable for permanent repair in all classes of road including motorways.
- **VIAFIX** hardens quickly to match performance of traditional macadam or asphalt, final settling may take a few

hours, especially in cold weather but trafficking can be instantaneous.

- **VIAFIX** may be overlaid with any road surfacing material, or sealed with surface dressing.
- **VIAFIX** will not be damaged by traffic, rain or frost when correctly applied.
- **VIAFIX** is available in three grade sizes: 0/3mm, 0/6mm and 0/10mm to match or compliment existing surfaces.

## DISCLAIMER

Our product instructions are general guidelines which may not apply in some circumstances and are not a guarantee of performance under all conditions. The user must satisfy themselves on the efficacy of the application or contact Viatec for advice on unusual applications.

# Net content: 14 kg

**VIA TEC UK Ltd.**  
Broadway House,  
3rd Avenue, Westfield Trading Estate,  
Radstock, Bath, BA3 4XD  
Tel.: 01761 415804

Email: [info@viatec-uk.com](mailto:info@viatec-uk.com), Web: [www.viatec-uk.com](http://www.viatec-uk.com)

20160321